



Figure 8. Current versus voltage (I-V) results from (a) Si and (b) SiC nanowires. The insets are Fowler-Nordheim plots of $\ln(I/E^2)$ against $(1/E)$.

Summary

A new method based on oxide-assisted growth has been developed that is capable of producing a bulk quantity of various semiconductor nanowires including Si and Ge. The presence of oxides in the target is a common and essential ingredient for the synthesis when using laser ablation or thermal evaporation techniques, in order that the targets are capable of generating semiconductor oxides in the vapor phase. Subsequent decomposition of the vapor-phase oxides at high temperatures plays a crucial role in the nucleation and growth of high-quality nanowires. In the case of Si, nanowires can be synthesized from metal-, SiO₂-, Ge-, or Fe₂O₃-containing Si targets or from SiO powders. Irrespective of the oxide type contained in the target, the resulting nanowires show no significant difference in their morphology and microstructure. Thick Si oxide shells are also present on the Si nanowires grown from the metal- and Fe₂O₃-containing targets. These semiconductor nanowires show unusual optical and field-emission characteristics that may

be exploited for potential applications. Thus the ability to synthesize large quantities of such nanowires from this powerful technique offers exciting possibilities for fundamental and applied research.

Acknowledgments

We thank I. Bello, C.S. Lee, D.P. Yu, Z.T. Zhou, H.L. Lai, F.C.K. Au, and K.W. Wong for their contributions to the work presented in this review. This work was supported by Strategic Research Grants from the City University of Hong Kong and the Research Grant Council of Hong Kong.

References

1. R.S. Wagner and W.C. Ellis, *Appl. Phys. Lett.* **4** (1964) p. 89.
2. E.I. Givargizov, *J. Cryst. Growth* **32** (1975) p. 20.
3. G.A. Boostma and H.J. Gassen, *J. Cryst. Growth*. **10** (1971) p. 223.
4. M. Gershenzo and R.M. Mikulyak, *J. Electrochem. Soc.* **108** (1961) p. 548.
5. N. Holonyak Jr., C.M. Wolfe, and J.S. Moore, *Appl. Phys. Lett.* **6** (1965) p. 64.
6. E.N. Laverko, V.M. Marakhonov, and S.M. Polyakov, *Sov. Phys. Crystallogr.* **10** (1966)

7. K. Hiruma, T. Katsuyama, K. Ogawa, G.P. Morgan, M. Koguchi, and H. Kakibayashi, *Appl. Phys. Lett.* **59** (1991) p. 431.
8. K. Hiruma, M. Yazawa, T. Katsuyama, K. Ogawa, K. Haraguchi, M. Koguchi, and H. Kakibayashi, *J. Appl. Phys.* **77** (1995) p. 447.
9. H.I. Liu, N.I. Maluf, and R.F.W. Pease, *J. Vac. Sci. Technol., B* **10** (1992) p. 2846.
10. H. Namatsu, S. Horiguchi, M. Nagase, and K. Kurihara, *J. Vac. Sci. Technol., B* **15** (1997) p. 1688.
11. Y. Wada, T. Kure, T. Yoshimura, Y. Sudou, T. Kobayashi, Y. Gotou, and S. Kondo, *J. Vac. Sci. Technol., B* **12** (1994) p. 48.
12. T. Ono, H. Saitoh, and M. Esashi, *Appl. Phys. Lett.* **70** (1997) p. 1852.
13. R. Hasunuma, T. Komeda, H. Mukaida, and H. Tokumoto, *J. Vac. Sci. Technol.*, **15** (1997) p. 1437.
14. Y.F. Zhang, Y.H. Zhang, N. Wang, D.P. Yu, C.S. Lee, I. Bello, and S.T. Lee, *Appl. Phys. Lett.* **72** (1998) p. 1835.
15. A.M. Morales and C.M. Lieber, *Science* **279** (1998) p. 208.
16. D.P. Yu, Z.G. Bai, Y. Ding, Q.L. Hang, H.Z. Zhang, J.J. Wang, Y.H. Zou, W. Qian, G.C. Xiong, H.T. Zhou, and S.Q. Feng, *Appl. Phys. Lett.* **72** (1998) p. 3458.
17. N. Wang, Y.H. Tang, Y.F. Zhang, D.P. Yu, C.S. Lee, I. Bello, and S.T. Lee, *Chem. Phys. Lett.* **283** (1998) p. 368.
18. N. Wang, Y.F. Zhang, Y.H. Tang, C.S. Lee, and S.T. Lee, *Appl. Phys. Lett.* **73** (1998) p. 3902.
19. N. Wang, Y.H. Tang, Y.F. Zhang, C.S. Lee, and S.T. Lee, *Phys. Rev. B* **58** (1998) p. 16024.
20. N. Wang, Y.H. Tang, Y.F. Zhang, C.S. Lee, I. Bello, and S.T. Lee, *Chem. Phys. Lett.* **299** (1999) p. 237.
21. S.W. Roberts, G.J. Parker, and M. Hempstead, *Opt. Mater.* **6** (1996) p. 99.
22. U. Setiowati and S. Kimura, *J. Am. Ceram. Soc.* **80** (1997) p. 757.
23. G. Hass and C.D. Salzberg, *J. Opt. Soc. Am.* **44** (1954) p. 181.
24. Ph. Buffat and J.P. Borel, *Phys. Rev. A* **13** (1976) p. 2287.
25. J.P. Borel, *Surf. Sci.* **106** (1981) p. 1.
26. Y.H. Tang, Y.F. Zhang, N. Wang, I. Bello, C.S. Lee, and S.T. Lee, *J. Appl. Phys.* in press.
27. K.W. Wong, X.F. Zhou, F.C.K. Au, H.L. Lai, C.S. Lee, and S.T. Lee (unpublished).
28. F.C.K. Au, K.W. Wong, Y.H. Tang, Y.F. Zhang, I. Bello, and S.T. Lee, *J. Appl. Phys. Lett.* in press. □

Advertisers in This Issue

	Page No.		Page No.
Chemat Technology, Inc.	35	MTS Systems Corporation	Inside back cover
EDAX, Inc.	4, 5	RBD Enterprises, Inc.	7
High Voltage Engineering	Inside front cover	Saint-Gobain Industrial Ceramics, Inc.	6
Huntington Mechanical Laboratories, Inc.	Outside back cover	Thermionics Vacuum Products	19
MDC Vacuum Products, Corp.	30		

For free information about the products and services offered in this issue, check www.mrs.org/publications/bulletin/advertisers or fill out and mail the Reader Service Card, or FAX it to 312-922-3165.